

DAFTAR PUSTAKA

1. Arifah A. Riyanto. (2003). *Teori Busana*. Bandung: Yapemdo.
 2. Baird, J. (2012). *Metric pattern cutting for women's wear*. John Wiley & Sons.
 3. Barthes, Roland. (1967). *The Language of Fashion*. Hill and Wang.
 4. Buku Pedoman Tugas Akhir. (2018). Politeknik STTT Bandung.
 5. Casanova, J. (2013). *The Fundamentals of Fashion Design* (2nd ed.). Bloomsbury Publishing.
 6. D. E. Steele. (2015). *Fashion and Its Social Agendas: Class, Gender, and Identity in Clothing*. University of Chicago Press.
 7. Gerschel, L. (2019). *Fashion History Lesson: Haute Couture Vs. Ready-to-Wear*.
 8. J. Ashdown, M. Dunbar, S. Sherratt, and J. Tierney (Eds.). (2019). *The Handbook of Clothing Material Culture*. Routledge.
 9. King, U. (2015). *Ready-to-wear and ready-to-work: A century of industry and labor in the apparel industry*. *The American Historical Review*
 10. Lidwell, W., Holden, K., & Butler, J. (2010). *Universal Principles of Design, Revised and Updated: 125 Ways to Enhance Usability, Influence Perception, Increase Appeal, Make Better Design Decisions, and Teach Through Design*. Rockport Publishers.
 11. Petrova, E., & Mason, R. (2019). *The role of innovation in the fashion industry: A meta-analysis of the literature*. *Journal of Fashion Marketing and Management: An International Journal*,
 12. R. B. Oliver and J. F. Tse. (2018). *The Dark Triad of Personality: Narcissism, Machiavellianism, and Psychopathy in Everyday Life*. Taylor & Francis.
 13. Sproat, K. (2018). *Ready-to-Wear*. In *The Berg Companion to*. Bloomsbury Academic.
 14. Swedlund, J. L., & Roark, P. (2006). *Cyanotype: Historical and Alternative Photography*. *Journal of Chemical Education*
 15. T. H. Kim and E. K. Kim. (2017). *The Influence of Social Media on Global Fashion Consumption*. *Journal of Global Fashion Marketing*, 8(4), 315-328.
 16. Wolff, Colette. (2000). *The Art of Manipulating Fabric*. New York: Platypus
- Indonesia Trend Forecasting. Fashion Trend 2023/2024: Co-Exist*

LAMPIRAN

Lampiran 1 Hasil Pengujian Serat

1. Uji Kualitatif Metode Pembakaran

a. Kain Poplin

Asap: Putih

Bau: Plastik dan Kertas

Sifat Pembakaran: Tidak meneruskan pembakaran

Sisa Pembakaran: Gumpalan keras



b. Kain Primisima

Asap: Putih

Bau: Kertas

Sifat Pembakaran: Meneruskan pembakaran

Sisa Pembakaran: Abu



c. Kain Organdi

Asap: Putih

Bau: Plastik

Sifat Pembakaran: Tidak meneruskan pembakaran

Sisa Pembakaran: Gumpalan keras

2. Uji Kualitatif Metode Pelarutan

a. Kain Poplin

- Metil Salisilat : Tidak larut pada kondisi biasa, larut sebagian pada kondisi dipanaskan

- H₂SO₄ 70% : Tidak larut pada kondisi biasa, larut sebagian
Kesimpulan: Kain Poplin merupakan campuran serat poliester dan kapas

b. Kain Primisima

- Metil Salisilat : Tidak Larut
- H₂SO₄ 70% : Larut

Kesimpulan: Kain Primisima merupakan 100% serat kapas.

c. Kain Organdi

- Metil Salisilat : Larut
- H₂SO₄ 70% : Tidak Larut

Kesimpulan: Kain Organdi merupakan 100% serat poliester.

Lampiran 2 Hasil Pengujian Tahan Luntur Warna

Pada busana Ready-To-Wear yang dibuat, hanya Kain Primisima dengan penerapan *cyanotype* yang memiliki warna


1. Tabel Hasil Uji Tahan Luntur Warna Terhadap Gosokan

Kain	Uji Tahan Luntur Warna Terhadap Gosokan	Skala	
		Basah	Kering
Kain Primisima dengan penerapan <i>cyanotype</i>	<i>Staining Scale</i>	4/5 (Baik)	4/5 (Baik)
	<i>Grey Scale</i>	4/5 (Baik)	5 (Baik)





2. Tabel Hasil Uji Tahan Luntur Warna Terhadap Pencucian


Kain	Uji Tahan Luntur Warna Terhadap Pencucian	Skala
Kain Primisima dengan penerapan <i>cyanotype</i>	<i>Staining Scale</i>	5 (Baik)
	<i>Grey Scale</i>	5 (Baik)




Lampiran 3 Peta Proses Penjahitan





Peta Proses Penjahitan Sleeves Attachment
Dibuat oleh Anissya Fauzia
10 Juli 2023
Nomor Peta 03



Peta Proses Penjahitan Tube Top
Dibuat oleh Anissya Fauzia
10 Juli 2023
Nomor Peta 04





Lampiran 4 Percobaan Penjemuran Cyanotype

No	Waktu Penjemuran	Keterangan Hasil
1	30 Menit	Warna biru yang dihasilkan pudar
2	40 Menit	Warna biru yang dihasilkan pekat
3	50 Menit	Warna biru yang dihasilkan pekat namun muncul bercak warna kecoklatan pada kain

Hasil Percobaan Penjemuran Cyanotype Selama 30 Menit



Hasil Percobaan Penjemuran Cyanotype Selama 40 Menit



Hasil Percobaan Penjemuran Cyanotype Selama 50 Menit

