

## LAMPIRAN

Lampiran 1 Data pengujian K/S

Sampel		Nilai K/S	
		Hasil	Rata-rata
Standar (non-simultan)		19,759	
Blanko		19,845	
A	1.1	19,759	19,716
	1.2	19,673	
B	1.1	19,255	19,7715
	1.2	20,288	
	2.1	19,845	19,4285
	2.2	19,012	
C	1.1	19,174	19,731
	1.2	20,288	
	2.1	19,42	19,809
	2.2	20,198	
D	1.1	19,42	19,7645
	1.2	20,109	
	2.1	19,093	19,736
	2.2	20,379	






Lampiran 2 Data pengujian kekuatan tarik

Sampel		Single Strength (gram)			Tenacity (cN/TEX)			Elongation (%)			
		Hasil	Rata-rata	Standar mutu	Hasil	Rata-rata	Standar mutu	Hasil	Rata-rata	Standar mutu	
Standar (proses non-simultan)		350	350		17,8		6	6			
		350					6				
		350					6				
Blanko		310	306,7		15,6		5	5			
		310					5				
		300					5				
A	1.1	350	350	351,7	17,8	17,85	6	6	6		
		350					6				
		350					6				
	1.2	350	353,3		17,9		6	6			
		360					6				
		350					6				
B	1.1	370	366,7	366,7	18,6	18,6	7	6,7	6,35		
		370					7				
		360					6				
	1.2	370	366,7		18,6		6	6			
		360					6				
		370					6				
	2.1	320	323,3	326,7	16,4	16,6	6	6	6		
							320			6	
							330			6	
		2.2	330		330		16,8	6		6	
								330			6
								330			6
C	1.1	350	350	348,4	17,8	17,7	6	6	6		
		350					6				
		350					6				
	1.2	350	346,7		17,6		6	6			
		340					6				
		350					6				
	2.1	350	350	353,4	17,8	17,95	6	6	6		
							350			6	
							350			6	
		2.2	360		356,7		18,1	6		6	
								360			6
								350			6
D	1.1	370	370	368,4	18,8	18,7	6	6	6		
		370					6				
		370					6				
	1.2	360	366,7		18,6		6	6			
		370					6				
		370					6				
	2.1	330	323,3	325	16,4	16,5	6	5,3	5,3		
							320			5	
							320			5	
		2.2	320		326,7		16,6	6		5,3	
								330			5
								320			5




Lampiran 3 Data hasil penilaian pegangan benang

No	Responden	Blanko	Skor													
			A		B				C				D			
			1.1	1.2	1.1	1.2	2.1	2.2	1.1	1.2	2.1	2.2	1.1	1.2	2.1	2.2
1	Adam	1	3	3	3	4	4	3	3	3	2	3	3	4	4	3
2	Ahmad	1	4	4	3	4	2	2	3	4	3	3	2	4	2	3
3	Alman	1	4	4	3	3	2	3	3	3	4	3	3	3	3	2
4	Aswati	2	2	3	4	3	2	2	4	3	2	3	3	4	2	3
5	Aulia	2	3	4	3	3	3	3	2	2	3	3	4	4	2	2
6	Dea	2	4	3	3	3	2	2	3	3	3	3	3	3	2	3
7	Dhea Nurkhoffah	3	3	4	3	4	3	4	4	3	3	4	3	3	2	2
8	Dwi	2	4	4	4	3	2	3	3	3	4	3	3	3	2	3
9	Endang	1	4	4	4	3	2	3	3	3	3	3	3	4	2	2
10	Guritno	3	3	3	3	2	2	2	2	2	3	2	1	3	2	3
11	Ida	1	4	3	3	4	2	2	3	4	3	3	3	3	2	2
12	Rizki	1	4	4	4	3	2	2	3	4	3	3	4	3	2	3
13	Rendi A.	3	3	3	3	2	3	3	4	3	3	3	2	3	4	4
14	Reynaldo	3	2	2	3	2	1	2	3	2	3	2	3	3	2	2
15	Roso	1	3	3	3	3	2	2	4	3	3	4	3	3	2	2
16	Rosyad	2	2	4	4	3	2	3	4	3	3	3	3	3	2	2
17	Sumitri	1	4	4	3	3	3	2	3	3	3	3	4	4	2	3
18	Tony S.	2	3	4	3	3	3	2	2	2	3	3	3	3	2	3
19	Viosa Diaz	2	3	2	3	2	2	3	3	3	3	3	4	4	4	4
20	Yanto	1	4	3	3	3	2	2	3	3	3	3	3	3	2	2
<b>Jumlah</b>		35	66	68	65	60	46	50	62	59	60	60	60	67	47	53
<b>Rata-rata</b>		1,75	3,3	3,4	3,25	3	2,3	2,5	3,1	2,95	3	3	3	3,35	2,35	2,65
			3,35		3,125		2,4		3,025		3		3,175		2,5	

Lampiran 4 Sampel hasil percobaan

Kode Sampel	Konsentrasi		Sampel Benang Hasil Percobaan	
	Albafix	Eskasoft		
Blanko	–	–		
Standar (Non-simultan)	0,50%	3,00%		
A (Simultan)	0,50%	3,00%		
B	1	0,75%	4,50%	
	2	0,25%	1,50%	

Lampiran 4 Sampel hasil percobaan (lanjutan)

Kode Sampel		Konsentrasi		Sampel Benang Hasil Percobaan
		Albafix	Eskasoft	
C	1	0,75%	3,00%	
	2	0,25%	3,00%	
D	1	0,50%	4,50%	
	2	0,50%	1,50%	