

LAMPIRAN

Lampiran 1 Data hasil Pengujian *Course Per Inch*

No	I	II	III	IV	V	VI	VII
1	23	21	20	20	19	19	23
2	21	19.5	20	20	19.5	19	24
3	22.5	20	19	19	20	19	23
4	23	20	20	19	20	19	23
5	23	20	20	19	20	20	23
6	23	21	20	20	20	19	23
7	22.5	21	19	20	20	19	23
8	22.5	20	20	20	19	19	23
9	22.5	21	20	20	19	20	23
10	23	21	20	20	20	20	24
Jumlah	226	204.5	198	197	196.5	193	232
Rata-rata	22.6	20.45	19.8	19.7	19.65	19.3	23.2
SD	0.6146363	0.59861	0.42164	0.48305	0.47434	0.48305	0.42164
CV	2.7196296	2.92719	2.12948	2.45201	2.41395	2.50283	1.8174
E	3.0775506	3.31242	2.40973	2.77471	2.73164	2.83222	2.05658

Lampiran 2 Data hasil Pengujian *Wale Per Inch*

No	I	II	III	IV	V	VI	VII
1	19	18	17	17.5	16	15.5	26
2	19.5	18	17.5	17	16	16	25
3	20	18	17.5	17	16	16	25
4	19.5	18	17.5	17	16	16	25
5	19.5	18	17	17.5	16	15.5	25
6	19.5	18	17.5	17.5	16	16	25
7	19.5	18	17.5	17	16	16	25
8	20	18	17.5	17	16	16	25
9	20	18	17.5	17	16	16	25
10	20	18	17.5	17	16	16	25
Jumlah	196.5	180	174	171.5	160	159	251
Rata-rata	19.65	18	17.4	17.15	16	15.9	25.1
SD	0.337474279	0	0.210819	0.241523	0	0.210819	0.316228
CV	1.717426355	0	1.211601	1.408297	0	1.325903	1.259872
E	1.943450875	0	1.371055	1.593638	0	1.5004	1.425679

Lampiran 3 Data hasil pengujian berat kain

No	I	II	III	IV	V	VI	VII
1	211.5	209.5	206	202	184.5	184	139
2	209.5	207	204.5	201.5	179.5	179.5	136
3	208	208.5	202	200	183	182	136.5
Jumlah	629	625	612.5	603.5	547	545.5	411.5
Rata-rata	209.667	208.333	204.167	201.167	182.333	181.833	137.167
SD	1.75594	1.25831	2.02073	1.04083	2.5658	2.25462	1.60728
CV	0.83749	0.60399	0.98974	0.5174	9.16357	1.23994	1.17177
E	0.94771	0.68348	1.12	0.58549	10.3696	1.40312	1.32598

Lampiran 4 Data pengujian ketebalan kain

No	I	II	III	IV	V	VI	VII
1	2.18	2.21	2.32	2.27	2.34	2.37	2.11
2	2.19	2.2	2.27	2.33	2.32	2.38	2.12
3	2.18	2.24	2.28	2.27	2.31	2.36	2.19
4	2.15	2.24	2.3	2.33	2.32	2.38	2.14
5	2.19	2.29	2.27	2.32	2.31	2.35	2.14
6	2.18	2.25	2.27	2.32	2.33	2.36	2.15
7	2.18	2.25	2.28	2.32	2.32	2.34	2.11
8	2.19	2.24	2.28	2.32	2.33	2.38	2.15
9	2.18	2.25	2.3	2.33	2.34	2.38	2.18
10	2.19	2.23	2.28	2.33	2.31	2.35	2.18
Jumlah	21.81	22.4	22.85	23.14	23.23	23.65	21.47
Rata-rata	2.181	2.24	2.285	2.314	2.323	2.365	2.147
SD	0.01197219	0.0244949	0.016499	0.023664	0.011595	0.015092	0.029078
CV	0.548931224	1.09352221	0.722064	1.022659	0.49914	0.638153	0.028231
E	0.621174156	1.23743687	0.817092	1.157247	0.56483	0.722138	0.031947

Lampiran 5 Data hasil pengujian daya tembus udara

No	I	II	III	IV	V	VI	VII
1	6.05	7.65	8.06	8.93	10.4	9.53	13.7
2	6.71	7.52	8.45	7.79	9.91	8.13	14.5
3	6.31	6.45	7.02	7.59	7.34	8.05	12.3
4	6.68	9.35	9.14	9.98	8.82	9.92	15.1
5	7.38	8.58	8.74	8.87	9.65	9.47	14.3
6	6.63	7.86	8.88	8.68	8.78	9.84	12.6
7	6.48	8.42	7.72	7.96	9.89	9.37	14.2
8	7.22	9.16	7.46	8.96	9.21	9.66	13.3
9	6.16	6.88	8.26	8.78	8.62	8.47	16.1
10	6.82	7.14	8.59	7.86	7.44	8.94	12.9
Jumlah	66.44	79.01	82.32	85.4	90.06	91.38	139
Rata-rata	6.644	7.901	8.232	8.54	9.006	9.138	13.9
SD	0.42633	0.96332	0.66962	0.73424	1.02528	0.6976	1.1804
CV	6.41682	12.1924	8.1344	8.59768	11.3844	7.63401	8.49205
E	3.97718	7.55693	5.04175	5.3289	7.05615	4.73161	5.26343

Lampiran 6 Uji Normalitas data daya tembus udara

Tests of Normality							
	variasi	Kolmogorov-Smirnov ^a			Shapiro-Wilk		
		Statistic	df	Sig.	Statistic	df	Sig.
DTU	I	.140	10	.200*	.957	10	.753
	II	.117	10	.200*	.967	10	.859
	III	.128	10	.200*	.966	10	.855
	IV	.209	10	.200*	.924	10	.393
	V	.153	10	.200*	.928	10	.427
	VI	.230	10	.142	.883	10	.142
	VII	.106	10	.200*	.970	10	.894

*. This is a lower bound of the true significance.

a. Lilliefors Significance Correction

Lampiran 7 Uji homogenitas data daya tembus udara

Test of Homogeneity of Variances					
		Levene Statistic	df1	df2	Sig.
DTU	Based on Mean	2.141	6	63	.061
	Based on Median	1.900	6	63	.095
	Based on Median and with adjusted df	1.900	6	53.419	.098
	Based on trimmed mean	2.132	6	63	.062