

LAMPIRAN

Lampiran 1 Hasil Pengujian Ketidakrataan Benang (U%) Sebelum Pencucian Apron

No	Nilai Ketidakrataan Benang (U%) Sebelum Pencucian (x_i)	$(x_i - \bar{x})^2$	thin	thick	neps
1	13,24	0,05	29	55	339
2	13,67	0,04	48	71	397
3	13,05	0,17	25	38	317
4	13,62	0,03	25	50	343
5	12,43	1,06	3	43	245
6	14,42	0,92	26	40	283
7	13,86	0,16	40	75	283
8	13,32	0,02	28	43	299
9	13,42	0,00	38	69	384
10	13,56	0,01	42	65	401
Jumlah	134,59	2,46			
\bar{x}	13,46	-			
Standar Deviasi	0,52	-			
Koefisien Variasi (%)	3,88	-			
Sampling Error (%)	2,58	-			

Lampiran 2 Hasil Pengujian Ketidakrataan Benang (U%) Sesudah Pencucian Apron

No	Nilai Ketidakrataan Benang (U%) Sesudah Pencucian (x_i)	$(x_i - \bar{x})^2$	thin	thick	neps
1	12,55	0,18	7	48	357
2	13,03	0,00	21	60	411
3	12,48	0,24	13	28	401
4	12,45	0,27	8	20	316
5	11,49	2,19	2	18	296
6	13,59	0,38	55	62	311
7	13,59	0,38	48	71	397
8	13,02	0,00	23	31	286
9	14,52	2,40	19	34	324
10	12,99	0,00	29	38	310
Jumlah		6,06			
\bar{x}	12,97	-			
Standar Deviasi	0,82	-			
Koefisien Variasi (%)	6,32	-			
Sampling Error (%)	4,20	-			

Lampiran 3 Tabel Nilai t

d.f	$t_{0.10}$	$t_{0.05}$	$t_{0.025}$	$t_{0.01}$	$t_{0.005}$	d.f
1	3,078	6,314	12,706	31,821	63, 657	1
2	1,886	2,920	4,303	6,965	9,925	2
3	1,638	2,353	3,182	4,541	5,841	3
4	1,533	2,132	2,776	3,747	4,604	4
5	1,476	2,015	2,571	3,365	4,032	5
6	1,440	1,943	2,447	3,143	3,707	6
7	1,415	1,895	2,365	2,998	3,499	7
8	1,397	1,860	2,306	2,896	3,355	8
9	1,383	1,833	2,262	2,821	3,250	9
10	1,372	1,812	2,228	2,764	3,169	10
11	1,363	1,796	2,201	2,718	3,106	11
12	1,356	1,782	2,179	2,681	3,055	12
13	1,350	1,771	2,160	2,650	3,012	13
14	1,345	1,761	2,145	2,624	2,977	14
15	1,341	1,753	2,131	2,602	2,947	15
16	1,337	1,746	2,120	2,583	2,921	16
17	1,333	1,740	2,110	2,567	2,898	17
18	1,330	1,734	2,101	2,552	2,878	18
19	1,328	1,729	2,093	2,539	2,861	19
20	1,325	1,725	2,086	2,528	2,845	20
21	1,323	1,721	2,080	2,518	2,831	21
22	1,321	1,717	2,074	2,508	2,819	22
23	1,319	1,714	2,069	2,500	2,807	23
24	1,318	1,711	2,064	2,492	2,797	24
25	1,316	1,708	2,060	2,485	2,787	25
26	1,315	1,706	2,056	2,479	2,779	26
27	1,314	1,703	2,052	2,473	2,771	27
28	1,313	1,701	2,048	2,467	2,763	28
29	1,311	1,699	2,045	2,462	2,756	29
30	1,310	1,697	2,042	2,457	2,750	30
31	1,309	1,696	2,040	2,453	2,744	31
32	1,309	1,694	2,037	2,449	2,738	32
33	1,308	1,692	2,035	2,445	2,733	33
34	1,307	1,691	2,032	2,441	2,728	34
35	1,306	1,690	2,030	2,438	2,724	35
36	1,306	1,688	2,028	2,434	2,719	36
37	1,305	1,687	2,026	2,431	2,715	37
38	1,304	1,686	2,024	2,429	2,712	38

Lampiran 4 Data Nilai Ketidakrataan Benang Ne1 40 di PT PINTEX

