

LAMPIRAN

Lampiran 1 Hasil Pengujian Kain

1. Pengujian Tahan Luntur Warna

a. Tahan Luntur Warna Terhadap Pencucian

Contoh Uji	Gray Scale	Staining Scale	
		Katun	Polyester
Kain Katun Prima (Kain Batik)	5	5	5
Kain Polyester	5	5	5
Kain Rayon	5	5	5

b. Tahan Luntur Warna Terhadap Gosokan

Contoh Uji	Gray Scale	Staining Scale	
		Katun	Polyester
Kain Katun Prima (Kain Batik)	5	5	5
Kain Polyester	5	5	5
Kain Rayon	5	5	5

c. Tahan Luntur Warna Terhadap Keringat Asam dan Basa

Contoh Uji	Staining Scale	
	Katun	Polyester
Kain Katun Prima (Kain Batik)	Asam : 2/3 Basa : 2/3	Asam : 4 Basa : 4
Kain Polyester	5	5
Kain Rayon	5	5

2. Pengujian Kualitatif (Pengujian Larutan)

No.	Contoh Uji	Gambar	Hasil Endapan Akhir	Hasil
1	Polyester		Terlarut habis oleh larutan Metil Salisilat	100% polyester
2	Katun Prima (Batik)		Terlarut habis oleh larutan H_2SO_4 70%	100% serat kapas
3	Rayon		Terlarut habis oleh larutan H_2SO_4	100% serat kapas