



LAMPIRAN 1

Pola yang digunakan dapat dilihat sebagai berikut:


1. Pola kemeja busana *look 1*



2. Pola rompi busana *look 1*




3. Pola rok busana *look 1*



4. Pola blus busana *look 2*



5. Pola slayer busana *look 2*



6. Pola rok busana *look 2*



LAMPIRAN 2

Data Pengujian

1. Gramasi kain

a. Kain primisima

$$\frac{100 \text{ cm} \times 100 \text{ cm}}{10 \text{ cm} \times 10 \text{ cm}} \times 0,9533 = 95,5 \text{ g/m}^2$$

b. Kain lurik

$$\frac{100 \text{ cm} \times 100 \text{ cm}}{10 \text{ cm} \times 10 \text{ cm}} \times 1,248 = 124,8 \text{ g/m}^2$$

2. Pengujian Serat

a. Uji kuantitatif dan kualitatif

Nama kain	keterangan	Gambar	
		Sebelum	Sesudah
Kain primisima	100% kapas Cara uji kualitatif pelarutan Larut sempurna dalam H ₂ SO ₄ 70%		
Kain lurik	100% kapas Cara uji kualitatif pelarutan		



	Larut sempurna dalam H ₂ SO 70%		
Kain amerikan drill	13% kapas 87% polyester Cara uji kuantitatif Menggunakan H ₂ SO 70%		
	Perhitungan	$\frac{0,70}{1,06} \times 100\% = 66,037$ $100\% - 66,037 = 33,9\%$	
Kain toyobo	33% rayon 67% polyester Cara uji kuantitatif Menggunakan H ₂ SO 59,5%		
	Perhitungan	$\frac{0,74}{1,08} \times 100\% = 68,518$ $100\% - 68,518 = 31,4\%$	


b. Uji mikroskop

Nama kain	Keterangan	Gambar	
		Pakan	Lusi
Kain amerikan drill	Pakan Silinder panjang, bitnik-bintik dan bergaris halus mengikuti arah serat		
	Lusi Silinder panjang, bintik bintik		
Kain toyobo	Pakan Silinder panjang, bintik-bintik		
	Lusi Silinder panjang, bitnik-bintik dan bergaris halus mengikuti arah serat		

3. Pengujian tahan luntur warna

a. Uji tahan luntur warna terhadap keringat

Contoh Uji	Uji keringat asam	
	Kapas	Poliester
	Staining color	
Kain pencelupan		
	3/4	3
	Greyscale color	
		
	3	
Kain lurik	Staining color	
		
	4/5	4/5
	greyscale	
		
	4/5	
Contoh Uji	Uji keringat basa	
	Kapas	Poliester
	Staining color	

Kain primisima pencelupan		
	Greyscale color	
		
Kain lurik	Staining color	
		
	greyscale	
		

b. Tahan luntur warna terhadap pencucian

Contoh Uji	Kapas	Poliester
	Staining color	
Kain pencelupan		

			4/5
	3/4		
	Greyscale color		
Kain lurik			3
	Staining color		
			4/5
	greyscale		
			4/5