

DAFTAR LAMPIRAN

1. Hasil data dari pengujian kekuatan tarik benang

Benang Katun Variasi Lampu 25 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	1,43
2	1,52
3	1,37
4	1,49
5	1,44
Σ	1,45
SD	0,057879185
CV%	3,991667898
E%	3%

Benang Katun Variasi Lampu 40 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	1,97
2	2,02
3	1,98
4	1,78
5	1,6
Σ	1,87
SD	0,177200451
CV%	9,475959971
E(%)	8%

Benang Katun Variasi Lampu 60 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	2,35
2	2,1
3	2,19
4	2,25
5	2,28
Σ	2,234
SD	0,094498677
CV%	4,230021363
E	4%

Benang Katun Variasi Standard	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	3,08
2	3,22
3	3,04
4	3,13
5	3,31
Σ	3,156
SD	0,109224539
CV%	3,460853592
E%	5%

2. Hasil data dari pengujian kekuatan tarik benang

Benang Rayon Variasi Lampu 25 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	1,42
2	1,4
3	1,53
4	1,45
5	1,5
	1,46
SD	0,054313902
CV%	3,720130305
E%	2%

Benang Rayon Variasi Lampu 40 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	1,84
2	1,72
3	1,66
4	1,78
5	1,76
Σ	1,752
SD	0,067230945
CV%	3,83738272
E%	3%

Benang Rayon Variasi Lampu 60 Watt	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	1,94
2	1,99
3	1,97
4	1,91
5	1,97
Σ	1,956
SD	0,031304952
CV%	1,600457653
E%	1%

Benang Rayon Variasi Standard	
Beban 500 g	
Sample	Kekuatan Tarik (N)
1	2,32
2	2,43
3	2,38
4	2,35
5	2,42
Σ	2,38
SD	0,046368092
CV%	1,94823918
E%	2%