

Lampiran 1

Data hasil pengujian *sliver drawing* dengan penyetelan jarak jepit 38 mm.

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 29mm 100%					
DF. 2	FINISHER SETT BOTT ROLL 38					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cont %
	%	%	%	%	%	%
1	1.46	1.83	0.34			0.0
Mean	1.46	1.83	0.34			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 29mm 100%					
DF. 2	FINISHER SETT BOTT ROLL 38					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cont %
	%	%	%	%	%	%
1	1.41	1.80	0.38			0.0
Mean	1.41	1.80	0.38			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 29mm 100%					
DF. 2	FINISHER SETT BOTT ROLL 38					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cont %
	%	%	%	%	%	%
1	1.60	2.02	0.52			0.0
Mean	1.60	2.02	0.52			0.0
CV						
Q95						

Lampiran 2

Data hasil pengujian *sliver drawing* dengan penyetelan jarak jepit 40 mm.

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 28mm 100%					
DF. 2	FINISHER SETT BOTT ROU. 40					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnt ±
	%	%	%	%	%	%
1	1.51	1.89	0.39			0.0
Mean	1.51	1.89	0.39			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 28mm 100%					
DF. 2	FINISHER SETT BOTT ROU. 40					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnt ±
	%	%	%	%	%	%
1	1.48	1.86	0.33			0.0
Mean	1.48	1.86	0.33			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class	Sliver		
Uster Statistics						
Fiber	Cotton 4Micr 28mm 100%					
DF. 2	FINISHER SETT BOTT ROU. 40					
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnlt ±
	%	%	%	%	%	%
1	1.43	1.78	0.29			0.0
Mean	1.43	1.78	0.29			0.0
CV						
Q95						

Lampiran 3

Data hasil pengujian *sliver drawing* dengan penyetelan jarak jepit 42 mm.

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class Sliver			
Uster Statistics						
Fiber	Cotton 4Micr 29mm 100%					
DF. 2 FINISHER SET BOTT ROLL 42						
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnt ±
	%	%	%	%	%	%
1	1.88	2.11	0.23			0.0
Mean	1.88	2.11	0.23			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING						
Article	COTTON		Material class		Sliver	
Uster Statistics						
Fiber	Cotton 4Micr 29mm 100%					
DF. 2 FINISHER SETT BOT TROLL 42						
Total tests : 1 / 1 Single test(s)						
Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnt ±
	%	%	%	%	%	%
1	1.88	2.14	0.74			0.0
Mean	1.88	2.14	0.74			0.0
CV						
Q95						

DETAIL TEST USTER SLIVER AND ROVING

Article COTTON Material class Sliver

Uster Statistics

Fiber Cotton 4Micr 29mm 100%

DF. 2 FINISHER SET BOTT ROLL 42

Total tests : 1 / 1 Single test(s)

Nr	U%	CVm	CVm 1m	CVm 3m	CVm 10m	Rel. Cnt ±
	%	%	%	%	%	%
1	1.76	2.20	0.31			0.0
Mean	1.76	2.20	0.31			0.0
CV						
Q95						