



LAMPIRAN


Lampiran 1 Data pengujian hasil uji tahan gosok benang *single sheet*



Lampiran 2 Data pengujian hasil uji tahan gosok benang *double sheet*



Lampiran 3 Data pengujian hasil uji tahan gosok benang *triple sheet*



Lampiran 4 Data Pengujian Hairiness Metode *Single Sheet*

No. Of Test	Diatas 0,5		Result	Diatas 1,5		Result
1	378	119	497	29	5	34
2	436	121	557	23	11	34
3	340	155	495	37	11	48
4	311	121	432	35	15	50
5	286	178	464	30	23	53
6	379	200	579	58	31	89
7	264	210	474	31	25	56
8	234	224	458	32	27	59
9	212	109	321	15	10	25
10	158	115	273	18	11	29
Result Total			4550			477
Average			455			48
Max			579			89
Min			273			25

Lampiran 5 Data Pengujian Hairiness Metode *Double Sheet*

No. Of Test	Diatas 0,5		Result	Diatas 1,5		Result
1	157	124	281	23	20	43
2	155	104	259	17	12	29
3	118	86	204	16	6	22

4	176	85	261	15	6	21
5	273	103	376	15	12	27
6	335	80	415	13	2	15
7	270	93	363	22	6	28
8	186	100	286	20	23	43
9	235	96	331	12	8	20
10	218	94	312	28	9	37
Result Total	3088			285		
Average	309			29		
Max	415			43		
Min	204			15		

Lampiran 5 Data Pengujian Hairiness Metode *Triple Sheet*

No. Of Test	Diatas 0,5		Result	Diatas 1,5		Result
1	135	106	241	8	21	29
2	137	57	194	3	3	6
3	68	61	129	3	1	4
4	125	53	178	7	4	11
5	164	45	209	7	1	8
6	122	448	570	7	5	12
7	165	64	229	8	6	14
8	390	131	521	18	13	31
9	305	102	407	20	6	26
10	352	161	513	28	12	40
Result Total	3191			181		
Average	319			18		
Max	570			40		
Min	129			4		