

LAMPIRAN

No	Kekuatan Tarik Kain dengan Run-in 2220		Kekuatan Mulur Kain dengan Run-in 2220	
	Wale	Course	Wale	Course
1.	79,1	75,3	14,115	14,102
2.	79,4	75,5	14,174	14,055
3.	79,3	75,4	14,188	14,032
4.	79,1	75,5	14,144	14,076
5.	79,3	75,1	14,165	14,032
Σ	396,2	376,8	70,786	70,297
$\bar{x}$	79,24	75,36	14,157	14,059
SD	0,134	0,168	0,028	0,03
KV	0,16%	0,22%	0,19%	0,21%

Lampiran 1 Kekuatan tarik dan mulur kain dengan run-in 2220

No	Kekuatan Tarik Kain (N) dengan Run-in 2215		Kekuatan Mulur Kain (%) dengan Run-in 2215	
	Wale	Course	Wale	Course
1.	81,2	77,9	14,848	14,548
2.	81,5	77,9	14,774	14,574
3.	81,5	78,3	14,721	14,621
4.	81,3	77,8	14,848	14,548
5.	81,6	78,1	14,874	14,574
Σ	407,1	390	74,065	72,865
$\bar{x}$	81,42	78	14,813	14,573
SD	0,164	0,2	0,063	0,029
KV	0,2%	0,25%	0,42%	0,19%

Lampiran 2 kekuatan tarik kain dengan run-in 2215

No	Kekuatan Tarik Kain (N) dengan Run-in 2210		Kekuatan Mulur Kain (%) dengan Run-in 2210	
	Wale	Course	Wale	Course
1.	83,3	80,2	15.199	15.139
2.	83,3	80,4	15.159	15.061
3.	83,2	80,4	15.199	15.110
4.	82,9	80,3	15.295	15.077
5.	83,5	80,2	15.159	15.065
Σ	416,2	401,5	76.011	75.452
$\bar{x}$	83,24	80,3	15.202	15.09
SD	0,219	0,1	0,055	0,448
KV	0,26%	0,12%	0,36%	2,9%

Lampiran 3 Kekuatan tarik kain dengan run-in 2210



Lampiran 4 Pengujian kekuatan tarik kain

No	Uji CPI dan WPI dengan Run-in 2220	
	CPI	WPI
1.	38,5	33
2.	38,5	33,5
3.	38	33,5
4.	38	33
5.	38,5	33,5
Σ	191.5	166.5
$\bar{x}$	38.3	33.3
SD	0,273	0,273
KV	0,71%	0,81%

Lampiran 5 Data hasil pengujian cpi dan wpi dengan run-in 2220 mm

No	Uji CPI dan WPI dengan Run-in 2215	
	CPI	WPI
1.	39,5	34
2.	39	34,5
3.	39	34
4.	39,5	34
5.	38,5	34,5
Σ	195.5	172
$\bar{x}$	39.1	34.4
SD	0,353	0,418
KV	0,95%	1,21%

Lampiran 6 Data hasil pengujian cpi dan wpi dengan run-in 2215 mm

No	Uji CPI dan WPI dengan Run-in 2210	
	CPI	WPI
1.	39,5	35,5
2.	39,5	35
3.	39,5	35
4.	40	35
5.	40	35,5
Σ	198.5	176
$\bar{x}$	39.7	35.2
SD	0,273	0,273
KV	0,68%	0,77%

Lampiran 7 Data hasil pengujian cpi dan wpi dengan run-in 2210 mm

Pengujian	Nomor Benang		Kekuatan Tarik		Tahan Gosok	
Jenis Benang	75/36 RCL	75/36 ORI	75/36 RCL	75/36 ORI	75/36 RCL	75/36 ORI
Rata-rata	80,77 D	81,38 D	248 kgf	291 kgf	144 Gosokan	1480,3 Gosokan

Lampiran 8 Data pengujian benang

