

LAMPIRAN

Lampiran 1. Data Pengujian Gramasi

Sample	Jeratan Plain (gram/m ²)	Jeratan Rib 2x2 (gram/m ²)	Jeratan Rib 4x4 (gram/m ²)
1.	88,35	128,97	106,63
2.	122,88	116,7	103,58
3.	99,52	126,94	113,74
4.	98,50	132,01	108,66
5.	111,70	118,81	111,47
Mean	104,19	124,68	108,81
SD	6,04	2,95	1,78
CV (%)	5,79	2,36	1,63

Lampiran 2. Data Pengujian Daya Serap Cara Tetes

Sample	Jeratan Plain (s)	Jeratan Rib 2x2 (s)	Jeratan 4x4 (s)
1.	1,91	3,1	3,55
2.	1,79	2,93	2,34
3.	1,5	2,41	3,31
4.	2,18	3,41	4,16
5.	2,35	2,61	3,9
6.	1,79	3,53	4,15
7.	2,05	3,45	4,05
8.	2,39	3,5	4,4
9.	2,15	3,4	3,15
10.	2,07	3,75	3,5
Mean	2,01	3,2	3,2
SD	0,12	0,033	1,19
CV (%)	6,29	1,03	37,23

Lampiran 3. Data Hasil Uji Normalitas dan Homogenitas gramasi

Tests of Normality							
	variasi jeratan	Kolmogorov-Smirnov ^a			Shapiro-Wilk		
		Statistic	df	Sig.	Statistic	df	Sig.
variasi pengujian gramasi	plain	.237	5	.200*	.961	5	.815
	rib 2x2	.233	5	.200*	.908	5	.458
	rib 4x4	.160	5	.200*	.982	5	.945

*. This is a lower bound of the true significance.

a. Lilliefors Significance Correction

Tests of Homogeneity of Variances

		Levene Statistic	df1	df2	Sig.
variasi pengujian gramasi	Based on Mean	4.254	2	12	.040
	Based on Median	1.464	2	12	.270
	Based on Median and with adjusted df	1.464	2	5.949	.304
	Based on trimmed mean	4.136	2	12	.043

Lampiran 4. Data Hasil Uji Normalitas Dan Homogenitas Daya Serap

Tests of Normality

	variasi jeratan	Kolmogorov-Smirnov ^a			Shapiro-Wilk		
		Statistic	df	Sig.	Statistic	df	Sig.
nilai pengujian daya serap	Plain	.146	10	.200*	.962	10	.806
	Rib 2x2	.270	10	.038	.899	10	.213
	Rib 4x4	.157	10	.200*	.925	10	.400

*. This is a lower bound of the true significance.

a. Lilliefors Significance Correction

Tests of Homogeneity of Variances

		Levene Statistic	df1	df2	Sig.
nilai pengujian daya serap	Based on Mean	2.730	2	27	.083
	Based on Median	2.028	2	27	.151
	Based on Median and with adjusted df	2.028	2	21.791	.156
	Based on trimmed mean	2.699	2	27	.085